# **UCY ENERGY**

### UCY business services & trading (Germany) GmbH

YOU SEE SEE

www.ucy-energy.com

# PSF-CI05-CR Product Data Sheet

Item number: 60-036

#### **General Information**

Sulphate of Potash 52 (+45) 52 %  $K_2O$ , water-soluble potassium oxide (=43.2 % K) 45 %  $SO_3$ , water-soluble sulphur trioxide (=18 % S)

**PSF-CI05-CR** is a concentrated potassium and sulphur fertilizer with improved handling and spreading characteristics due to the crystalline structure. It is particular recommended to increase yield and quality of tobacco and other chloride sensitive crops e.g. vegetables and fruits. Moreover **PSF-CI05-CR** is the preferred form of potassium for salt affected soils because it is virtually free of chloride and has a low salt index.

The product is made from crude potassium salt of natural origin and is permitted for use in organic farming according to the Regulations (EC) No 834 / 2007 and (EC) No 889 / 2008.

## **Chemical Analysis**

Parameter	Unit	Typical value
Potassium Sulphate (K <sub>2</sub> SO <sub>4</sub> )	%	97.1
Other Sulphates (MgSO <sub>4</sub> , CaSO <sub>4</sub> )	%	1.7
Chlorides (KCl, NaCl)	%	0.6
Others, mainly Water of Crystallization	%	0.4
Moisture	%	0.2

#### **Granulometry**

Parameter		Unit	Typical value
Tyler Mesh +20	> 0.85 mm	%	4
Tyler Mesh 32 – 20	0.5 – 0.85 mm	%	23
Tyler Mesh 60 – 32	0.25 – 0.5 mm	%	42
Tyler Mesh 100 – 60	0.15 – 0.25 mm	%	18
Tyler Mesh -100	< 0.15 mm	%	13
SGN		%	36

- continue on page 2 -

E-mail: <u>info@ucy-energy.com</u> <u>www.ucy-energy.com</u>

# **UCY ENERGY**

# UCY business services & trading (Germany) GmbH



www.ucy-energy.com

- page 2 -

# **Storage**

Parameter	Unit	Typical value
Bulk Density	$kg / m^3$	approx. 1,500
Bulk Density	lbs / ft³	approx. 94
Bulk Density (packed)	$kg / m^3$	approx. 1,650
Bulk Density (packed)	lbs / ft³	approx. 103
Angle of Repose	o	approx. 30

The product is to be kept dry and covered with a plastic tarpaulin to protect from moisture. Where bulk product is stored, steel joists and columns should be protected from corrosion, as well as the floor and the walls should be furnished with a protective coating. Wooden walls and roof girders have proved to be particularly durable.

www.ucy-energy.com